



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A22C 13/00	A1	(11) International Publication Number: WO 00/67582 (43) International Publication Date: 16 November 2000 (16.11.00)
(21) International Application Number: PCT/CA00/00565 (22) International Filing Date: 8 May 2000 (08.05.00) (30) Priority Data: 2,271,361 7 May 1999 (07.05.99) CA (71)(72) Applicants and Inventors: MACQUARRIE, Reg [CA/CA]; 44 Belcourt Avenue, Barrie, Ontario L4M 4E4 (CA). SCHUPP, Kurt [CA/CA]; Apt. 201, 1071 Queens Avenue, Oakville, Ontario L6H 2R5 (CA). TAYLOR, Peter [CA/CA]; 5 Idared Road, Carlisle, Ontario L0R 1H3 (CA). (74) Agents: MITCHELL, Randall, S. et al.; Ridout & Maybee, Suite 2400, One Queen Street East, Toronto, Ontario M5C 3B1 (CA).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: EDIBLE CASING FILM FORMULATION (57) Abstract Edible films incorporating carrageenan in conjunction with Konjac and/or Gellan gums have been prepared as substitutes for edible collagen film currently used in meat processing. Compositions according to the present invention overcome the inherent thermoreversibility of carrageenan gel and do not disintegrate from exposure to hot or boiling water. The film can readily be processed to form casing, bags or other packaging useful in the food industry.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

EDIBLE CASING FILM FORMULATION**Background of the Invention**

For a number of years, edible films have been used to replace membranes and casings made of animal viscera, in the production of smoked meat products such as ham and sausages. Currently available edible films include collagen films, modified cellulose films and carrageenan-based films.

Collagen films are composed of edible collagen, plasticized with glycerol or other polyols. They are manufactured by extrusion onto a belt followed by drying to remove the moisture. The collagen slurry is applied to the belt cold, and requires high-temperature drying to remove all the excess moisture and bring the film to a final moisture content of approximately 10%. Apart from the difficulty in processing films of this kind, these materials can bring about allergic reactions in certain consumers. Too, being derived from the coum layer of beef or pork, collagen may be an unacceptable casing or film material for religious and dietary reasons.

Modified cellulose films are for the most part composed of modified hydroxypropyl methylcellulose. To date, almost all films of this kind which have been produced are cold water-soluble films which begin to disintegrate on contact with water. For this reason, they have not been used in meat processing.

Carrageenan is a polyanionic polysaccharide derived from red algae. The material is an excellent film-former and has been used in the formulation of edible food packaging films (U.S. Patent No. 4,851,394) and heat-sealable edible films (U.S. Patent No. 5,089,307 - Ninomiya et al.). Films composed primarily of carrageenan additionally exhibit excellent strength, are not soluble in cold water and bind well to meat substrates.

However, because carrageenan forms a thermoreversible gel, films composed of a predominant carrageenan proportion tend to disintegrate in hot water, i.e. above 70°C. The hot carrageenan aqueous solution
5 then re-gels upon contact with cooler water, less than 50°C.

It was one of our objectives to develop carrageenan-based films which can effectively and economically replace edible collagen films currently utilized in ham
10 and sausage production, while providing high yields and high-quality product.

Collagen film is typically wrapped around hams during production, for ease in netting removal after the ham has been cooked. Collagen films appear to the
15 consumer to be part of the ham after cooking and, indeed, are usually not taken note of by the average consumer. Many styles of meats are processed using collagen films, including various ham, chicken and turkey products.

General Description and Objects of the Invention

20 It is an object of the present invention to provide polysaccharide films which would function well by satisfying all of the following key attributes:

- composed of food ingredients which meet Food Chemical Codex Specifications and are approved for
25 usage, i.e. GRAS rated in the United States (generally regarded as safe).
- a film that would maintain its composition during the cooking cycle, until the ham forms its own natural protein skin.
- 30 - after cooking, film adheres to the finished product, in that it does not fully disintegrate after a prolonged exposure to hot water or steam.
- film is tender to eat following processing of the meat product.

-3-

- film binds to the meat surface during and subsequent to processing.
- film is permeable to flavouring smoke.
- film imparts an appealing shine and colour to the cooked product.

We have found that excellent properties for edible films can be achieved by including, along with the carrageenan, suitable non-thermoreversible gel-forming polymers, preferably Konjac and Gellan gums. Konjac is extracted from the konjac tuber. This polysaccharide hydrates immediately and can form either thermoreversible or non-thermoreversible gels, depending on the conditions under which the gel is formed. Gellan gum is a polysaccharide gum produced from bacterial fermentation. It is a strong gel former and produces gels that are non-thermoreversible in the presence of Ca^{+2} and other multivalent anions. Both Konjac and Gellan gums are edible and GRAS rated. We observed that Konjac tends to form gels having a higher degree of elasticity than Gellan, which forms gels having a more brittle texture.

According to present invention, edible films and casing materials comprise a polymer base of carrageenan/Konjac/Gellan, and also a suitable starch, alginate or other polysaccharide, depending on the specific attributes required.

Starch functions to reduce water absorption of the film and it is preferred that a high-amylose starch be used, as high-amylose starch is inherently a better film-former than other starches.

"Alginate" herein refers to the alginates which are commonly used in the food industry, namely polypropylene glycol alginate, sodium alginate or calcium alginate. Alginate in compositions according to the present

-4-

invention tend to produce strong films exhibiting good adhesion.

Specific methods and formulations are described in more detail below, but generally we have found the following compositions to provide useful edible films:

Component	Suggested Range	
	Low (wt.%)	High (wt.%)
Carrageenan	2	35
Gellan*	0	35
10 Konjac*	0	35
Locust bean gum (LBG)	0	10
Protein	0	15
Starch**	0	20
Alginate**	0	35
15 Sodium Citrate	1	5
Sorbitan Monostearate	0.25	3
Glycerol	1.0	35
Other Plasticizer†	0	25
Water	8	35

20 ** total of Gellan & Konjac gums should be no less than about 5 wt% and up to about 35 wt%

* total of starch + alginate should be no less than about 5 wt% and up to about 35 wt%

† polyhydric alcohols, other than glycerol

25 The synergistic effects of the main polymers, Gellan Konjac and carrageenan, function to produce a film of high tensile strength, hot and cold water resistance and gum substrate adherence.

30 The use of a protein source is desirable to provide the film with both improved adhesion and shine functionality. The presence of some (at least about 5%) of alginatge or starch component is necessary to give sufficient film casing adhesion.

35 Other polysaccharides, as discussed below, may be added to impart specific desired properties to the film. Glyerol was added for its elasticizing effects.

-5-

Optionally, calcium chloride or potassium carbonate may be utilized to improve the film strength and hot water resistance.

5 From other formulations tested it is possible to significantly alter the relative amounts of each gel-forming polymer in the film to produce films exhibiting some varying degree of hot water solubility.

Detailed Description of the Invention

10 Polymer solutions were prepared for film casting as follows: glycerol or other plasticizers were added to the requisite amount of hot water. While maintaining the solution at an elevated temperature (80-90° C), then the dry ingredients were added and the solution vigorously mixed to homogeneity. The polymer solution was then
15 continuously mixed under slow agitation for 1-2 hours to remove trapped air bubbles.

Once the polymer solution appeared to be smooth and free of lumps, it was cast into film, using either a casting box or with a standard draw down bar. Care must
20 be taken to ensure that the hot solution is cast in a uniform thin layer. In all of the experimental examples given below, film was formed by drawing the solution down onto a hot (90°C) stainless steel belt with a Gardener dye. The films were either air dried overnight at room
25 temperature, or dried over a hot water bath and then removed for testing.

Films produced this way would initially be tested for thickness using a micrometer (Gauge) and tensile/tear strength.

30 The methods for measuring tear strength and elongation are those specified in ASTM D638. Normally 5

-6-

specimens are tested from each of 5 samples with the following conditions

- 20lbf load cell
- Crosshead speed: 2 in./minute
- 5 • Die "C" cut specimens

Films that met these requirements would then be tested for hot water solubility by placing strips of the film in boiling water and then allowing the water to cool with the film sample in it. After cooling, the water
10 would then be drained off and non-solubilized material would be placed with the drain dish in the drying oven. If the film was reconstituted after drying then the film was deemed to have maintained its structure during exposure to the hot water. If the film was not resistant
15 to the water then it would become soluble and could be poured off. (Hence no film left after drying)

After a particular sample had been characterized as above, it would be subjected to the same process conditions under which commercial meats are produced. In
20 particular the film would be wrapped around a particular meat substrate (turkey, ham, chicken) and then the wrapped meat sample dried in a convection oven until a protein skin could be seen forming on the sample. After this the sample was transferred into a steam cooker for
25 the completion of cooking. The internal temperature of the meat sample would have to reach 70-80°C. After the completion of cooking, the sample was allowed to cool and the final product examined and results recorded. Samples were then packed away under vacuum for shelf-life
30 testing.

Films according to the invention which we tested on meat film wrap were also produced using the following polysaccharides, supplementary to starch and/or alginate, with Gellan and/or Konjac: agar, modified starches, guar

-7-

gum, cellulose gum, modified cellulose gum, gum arabic, pullian and xanthate.

In some of the formulations, the following proteins were included: gelatin, soya protein concentrate, soya protein isolate, whey protein concentrate, albumin, miscellaneous vegetable proteins, collagen and collagen hydrolysates.

The following general observations arose from our experiments:

- 10 (i) Either Gellan and/or Konjac is required for synergistic reaction with the carrageenan and other gums or polysaccharide to provide the desired hot water resistance. The proportion of Gellan and/or Konjac is that amount necessary to
15 modify carrageenan sufficiently to ensure that the film will not disintegrate upon exposure to hot water. Films could be made out of Konjac or Gellan alone, but these would be far less economical than the combination with other
20 polysaccharide and in any event would have inferior physical properties, e.g. poor film strength, susceptibility to hydration, etc.
- (ii) The presence of starch or alginate is essential in these compositions to impart proper adhesion at
25 the final film in its intended use as food film and casing.
- (iii) Added protein is highly advantageous, to ensure proper adherence of the film to the meat after completion of cooking and for the aforementioned
30 aesthetic purpose of mimicking the glossy appearance imparted by collagen.

The film compositions may also be modified by the addition of compounds for specific purposes, such as

1. anti-microbial;
2. release agents;
- 5 3. colourants (i.e. caramels, oleoresins and other synthetic or natural colourants - iron oxide);
4. flavors and spices.

With particular application to meat processing, black films can be produced using caramel, so that
 10 processors need no longer dip the meat products in a liquid caramel to obtain that colour.

Examples of Edible Film Formulations

Example 1

	<u>Component</u>	<u>Parts</u>
15	Gellan	15
	Locust bean gum	3
	Kappa carrageenan	3
	Konjac	8
	Sodium citrate	3
20	Calcium chloride	2
	Maltodextrin	10
	Glycerol	25
	Water	30

This film exhibited very high tensile strength (140
 25 kg/cm²) and good elongation (30%). The film showed outstanding resistance to tear and had excellent handling properties. The film could be removed from a meat product after cooking very easily. (low adhesion)

Example 2

	<u>Component</u>	<u>Parts</u>
30	Gellan	8
	Kappa carrageenan	10

- 9 -

	Konjac	3
	Locust bean gum	2
	HVP	7
	High amylose starch	9
5	Sodium citrate	1
	Sorbitan monostearate	1
	Glycerol	25
	Polyethylene glycol	5
	Water	29

10 The film exhibited very high tensile strength (135-140 kg/cm²) and elongation (35%), and in particular showed excellent wet tensile strength. Again this film showed outstanding mechanical handling properties and on a meat product had very good adhesion.

15 **Example 3**

	<u>Component</u>	<u>Parts</u>
	Gellan	4
	Kappa carrageenan	7
	Konjac	2
20	Locust bean gum	1
	HVP	7
	High amylose starch	14
	Glycerol	32
	Caramel	4
25	Water	29

30 This film exhibited good tensile strength (110 kg/cm²) and elongation (35%) and because of the addition of caramel powder was black in colour. The film had good adhesion properties as well as excellent mechanical handling properties.

Example 4

<u>Component</u>	<u>Parts</u>
------------------	--------------

-10-

	Gellan	10
	Locust bean gum	5
	Kappa carrageenan	8
	Hydrolyzed collagen	10
5	Maltodextrin	7
	Propylene glycol alginate	2
	Silicon dioxide	6
	Sodium citrate	2
	Potassium chloride	2
10	Glycerol	30

This film exhibited moderate tensile strength (100 kg/cm²) and good elongation (25%) and utilized collagen to give the film reasonable adhesion to a meat product.

Example 5

15	<u>Component</u>	<u>Parts</u>
	Carrageenan	30
	Konjac	15
	Alginate	20
	Glycerol	25
20	Water	10

This film was completely clear and exhibited a very high tensile strength (200 kg/cm²) with and elongation of 40%. It showed very high adhesion and could not be removed from the meat product after cooking.

25 Finally, an unexpected advantageous property which we observed in films made according to the invention was efficient heat sealability at 180°C, suggesting usefulness of these films as a replacement for hydroxypropyl methyl cellulose films in casings and food
30 pouches.

RIDOUT & MAYBEE
Toronto, Canada

Patent Agents

CLAIMS

1. A liquid composition for casting into an edible film, comprising a uniform mixture of from 2 to 35 wt.% of carrageenan, from 5 to 35 wt.% of a gum selected from the group consisting of Gellan gum and Konjac gum, from 5 to 35 wt.% of a polysaccharide selected from the group consisting of starches and alginates or combinations thereof, from 1 to 35 wt.% of glycerol, and from 8 to 35 wt.% of water.
2. A liquid composition according to claim 1, wherein said polysaccharide comprises a high-amylose starch.
3. A liquid composition according to claim 1, further comprising up to 10 wt.% of locust bean gum.
4. A liquid composition according to any one of claims 1 to 3, further comprising up to 15% of a protein selected from the group consisting of gelatin, soya protein concentrate, soya protein isolate, whey protein concentrate, albumin, vegetable protein, collagen and collagen hydrolysates.
5. A liquid composition according to any one of claims 1 to 4, further comprising up to 25 wt.% of a plasticizing polyhydric alcohol other than glycerol.
6. A liquid composition according to any one of claims 1 to 4, further comprising up to 5 wt.% of sodium citrate.
7. A liquid composition according to any one of claims 1 to 4, further comprising up to 2 wt.% of a salt selected from the group consisting of calcium chloride, potassium chloride and potassium carbonate.

-12-

8. An edible casing film prepared by forming and drying a film from a liquid composition according to any one of claims 1 to 7, wherein the proportion of Konjak gum and/or Gellan gum relative to the carrageenan present in said liquid composition has been selected such that the film produced does not disintegrate in water at a temperature in the range of from 70°C to 100°C.

INTERNATIONAL SEARCH REPORT

In national Application No
PCT/CA 00/00565

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A22C13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A22C C08J C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, WPI Data, EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 400 484 A (MITSUBISHI RAYON CO., LTD.) 5 December 1990 (1990-12-05) cited in the application page 3, line 51 -page 4, line 29 page 4, line 40 -page 5, line 10; claims 1-20	1-8
Y	EP 0 328 317 A (TAKEDA CHEMICAL INDUSTRIES, LTD.) 16 August 1989 (1989-08-16) page 2, line 19 - line 56 page 3, line 47 - line 55; claims 1-10 -/-	1-8

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

5 September 2000

Date of mailing of the international search report

15/09/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Permentier, W

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 00/00565

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>DATABASE WPI Section Ch, Week 9202 Derwent Publications Ltd., London, GB; Class A11, AN 1985-113524 XP002146576 & JP 60 055039 A (MITSUBISHI ACETATE CO., LTD.), 29 March 1985 (1985-03-29) abstract</p> <p>---</p>	1-8
Y	<p>GB 2 000 424 A (UCC) 10 January 1979 (1979-01-10) page 4, line 83 - line 94 page 4, line 124 -page 5, line 29; claims 1-28</p> <p>---</p>	1-8
A	<p>EP 0 709 030 A (HOECHST AG) 1 May 1996 (1996-05-01) column 2, line 8 -column 3, line 59; claims 1-10</p> <p>---</p>	1,4
A	<p>DATABASE WPI Week 9218 Derwent Publications Ltd., London, GB; AN 1992-147687 XP002146577 & JP 04 089841 A (MITSUBISHI RAYON CO., LTD.), 24 March 1992 (1992-03-24) abstract</p> <p>---</p>	1
A	<p>EP 0 795 270 A (VISKASE CORPORATION) 17 September 1997 (1997-09-17) claims 1-20</p> <p>---</p>	1
A	<p>DE 12 13 211 B (WOLFF & CO. AG) 24 March 1966 (1966-03-24) the whole document</p> <p>----</p>	1,7

INTERNATIONAL SEARCH REPORT

Information on patent family members

In ternational Application No

PCT/CA 00/00565

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 400484	A	05-12-1990	JP 2308760 A	21-12-1990
			JP 2308761 A	21-12-1990
			JP 2312555 A	27-12-1990
			JP 2714690 B	16-02-1998
			JP 2714701 B	16-02-1998
			JP 3180147 A	06-08-1991
			CA 2017402 A	23-11-1990
			CA 2244798 A	23-11-1990
			DE 69006260 D	10-03-1994
			DE 69006260 T	07-07-1994
			DK 400484 T	28-02-1994
			KR 9706117 B	24-04-1997
			US 5089307 A	18-02-1992
			US 5620757 A	15-04-1997
EP 328317	A	16-08-1989	CN 1036967 A	08-11-1989
			JP 1289457 A	21-11-1989
JP 60055039	A	29-03-1985	JP 1707889 C	27-10-1992
			JP 3077821 B	11-12-1991
GB 2000424	A	10-01-1979	AR 218497 A	13-06-1980
			AT 375815 B	10-09-1984
			AT 293880 A	15-02-1984
			AT 366236 B	25-03-1982
			AT 467478 A	15-08-1981
			AU 3747978 A	03-01-1980
			BE 868516 A	27-12-1978
			BR 7804068 A	10-04-1979
			CA 1106678 A	11-08-1981
			DE 2828296 A	04-01-1979
			DK 289178 A	29-12-1978
			ES 471176 A	16-01-1979
			FI 782023 A, B,	29-12-1978
			FR 2395912 A	26-01-1979
			IT 1097355 B	31-08-1985
			JP 1240900 C	26-11-1984
			JP 54011252 A	27-01-1979
			JP 59010788 B	12-03-1984
			NL 7806898 A	02-01-1979
			NO 782220 A, B,	29-12-1978
			NZ 187687 A	28-11-1980
			PH 13562 A	26-06-1980
			SE 439095 B	03-06-1985
			SE 7807276 A	29-12-1978
			ZA 7803674 A	25-07-1979
EP 709030	A	01-05-1996	DE 4438961 A	02-05-1996
			AT 183617 T	15-09-1999
			DE 59506682 D	30-09-1999
			ES 2137433 T	16-12-1999
			JP 8228666 A	10-09-1996
			US 5928737 A	27-07-1999
JP 4089841	A	24-03-1992	NONE	
EP 795270	A	17-09-1997	US 5695800 A	09-12-1997
			CA 2195694 A	14-09-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 00/00565

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 795270 A		CZ 9700745 A ZA 9702011 A	17-09-1997 30-07-1998
DE 1213211 B		NONE	